



Polyurethane Based, Styling Board Materials VAL-550

Filled polyurethane foam medium-light density, good dimensional stability and cell structure, easy workable by hand or milling machine, performing good shaving

Application	<ul style="list-style-type: none"> ● Cheap master model ● Foundry patterns 																		
Key Properties	<ul style="list-style-type: none"> ● Meddle density ● Good cell ● Easy workable ● Good shaving 																		
Physical Data	<table style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 70%;"></th> <th style="text-align: right;">Index</th> </tr> </thead> <tbody> <tr> <td>Density g/cm³ (approx.)</td> <td style="text-align: right;">0.55</td> </tr> <tr> <td>Color</td> <td style="text-align: right;">Light Brownt</td> </tr> <tr> <td>Compressive Strength MPa (DIN EN ISO 604)</td> <td style="text-align: right;">15-18 N/mm²</td> </tr> <tr> <td>Flexural strength, (DIN EN ISO 178)</td> <td style="text-align: right;">15-18 N/mm²</td> </tr> <tr> <td>Linear Thermal Expansion Co-efficient</td> <td style="text-align: right;">55-60 x10^{-6k-1}</td> </tr> <tr> <td>Abrasion resistance, Taber value</td> <td style="text-align: right;">1200-1300</td> </tr> <tr> <td>Shore D (DIN 53505)</td> <td style="text-align: right;">55-60</td> </tr> <tr> <td>Heat distortion, ISO 75</td> <td style="text-align: right;">83°C</td> </tr> </tbody> </table>		Index	Density g/cm ³ (approx.)	0.55	Color	Light Brownt	Compressive Strength MPa (DIN EN ISO 604)	15-18 N/mm ²	Flexural strength, (DIN EN ISO 178)	15-18 N/mm ²	Linear Thermal Expansion Co-efficient	55-60 x10 ^{-6k-1}	Abrasion resistance, Taber value	1200-1300	Shore D (DIN 53505)	55-60	Heat distortion, ISO 75	83°C
	Index																		
Density g/cm ³ (approx.)	0.55																		
Color	Light Brownt																		
Compressive Strength MPa (DIN EN ISO 604)	15-18 N/mm ²																		
Flexural strength, (DIN EN ISO 178)	15-18 N/mm ²																		
Linear Thermal Expansion Co-efficient	55-60 x10 ^{-6k-1}																		
Abrasion resistance, Taber value	1200-1300																		
Shore D (DIN 53505)	55-60																		
Heat distortion, ISO 75	83°C																		
Storage	Boards, finished tools and models should be stored flat in dry conditions. Temperature variations should be kept as moderate as possible.																		
Handling & Precaution	Valpolymer products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed.																		

Available dimension (length x wide x thickness/mm):

1500 X 500 X 50

1500 x 500 x 75

1500 x 500 x 100

www.val-tool.com

Valpolymer S.r.l

Via V. Alfieri, 1 - 24060 Credaro (Bg) - Italia Tel: +39 035 4265011 - FAX: +39 035 935203